



**Spectral density curves**




**Characteristic curves**




In order to simulate conditions closest to practical use, exposure was made under a 3200K tungsten light source, through a Fuji SC-41 ultraviolet absorbing filter. Processing was carried out under standard conditions and the three color densities were measured, producing the results indicated in the graph above.

**Contrast transfer function\***



**Spectral sensitivity curves**



Processing: Specified standard conditions  
 Densitometry: Arbitrary three color densities  
 Density: 0.40 above minimum density  
 Sensitivity: Reciprocal of exposure (ergs/cm<sup>2</sup>) required to produce specified density

**RMS granularity**

3.5 (1,000 times the data obtained from measurement taken at a visual diffuse density of 1.0 above minimum density, using a 48µm diameter aperture)